


Presto FF-C18

250 x 4.6 mm


Application

Polystyrenesulfonic acid

ポリスチレンスルホン酸



polystyrenesulfonic acid



Presto FF-C18, 250 x 4.6 mm

A: water / formic acid = 100 / 0.1

B: acetonitrile / formic acid = 100 / 0.1

3-20%B (0-60min)

0.4 mL/min (28MPa), 37°C, 20μL (10mg/mL, 0.1% HCOOH)